

**METHOD OF MAKING BASALT FIBRE**

Patent Number: ☐ WO9317975  
Publication date: 1993-09-16  
Inventor(s): KIBOL VIKTOR FEDOROVICH (RU)  
Applicant(s):: KIBOL VIKTOR F (RU)  
Requested Patent: RU2018491  
Application Number: WO1993RU00063 19930311  
Priority Number(s): SU19925031919 19920312  
IPC Classification: C03B37/00  
EC Classification: C03B37/05  
Equivalents:

---

**Abstract**

---

A method is proposed which includes feeding basalt rock to the melting zone, heating it in that zone up to a temperature of 1500-1600 DEG C and obtaining the melt. Then the melt is fed to a homogenization zone from which the homogenized melt having the viscosity of 100 poises comes to the fibre forming zone, where the drawing of the fibres is effected at a speed exceeding 3500 m/min.

---

Data supplied from the esp@cenet database - I2